

WPF-40CL Clear Polyester

FEATURES

outstanding clarity

•good glue adhesion

•very strong film

approved for direct food

contact

excellent chemical resis-

tance

DESCRIPTION: WPF-40CL is treated to promote good adhesion.

APPLICATIONS: Hardware, Cosmetics, Toys, Glassware, Pharmaceutical

Available gauges and Yields (in.sq/lb.)

Gauge: .00048 .00092 .00142 .002 .003 .004 .005 .007 Yield: 42,000 21,000 4,000 2,800 14,000 10,000 6,500 5,000

Property_	<u>Units</u>	Testing Method	Typical Value for
Gauge	mil		.00092
Yield	in.sq./lb.		21,000
Shrinkage	%	ASTM D2838	MD 2.5
(30 min @ 150°C)			TD 2.5
Modules	PSI MD	ASTM D 882	550,000
Co Efficient of Friction	Kinetic	ASTM D 1894	0.36
	Static		0.40
Density	g/cm ³	ASTM D1505	1.395
Haze	%	ASTM D1003	2.0 max.

Comments: All information contained herein represents the best information available to L&K Industries at the time of preparation. We make no guarantee of product performance and all recommendations with respect to its end use, either expressed or implied.